


Lesson 1

X-Rays & Diffraction



Nicola Döbelin
RMS Foundation, Bettlach, Switzerland

Electromagnetic Spectrum



X rays:


Wavelength λ : 0.01 – 10 nm
Energy: 100 eV – 100 keV

Interatomic distances in crystals:
typically 0.15 – 0.4 nm


Generation of X-radiation:
Shoot electrons on matter

Interference phenomena only
for features $\approx \lambda$

X-ray Tube




X-ray Tube



Generation of X-rays

Accelerated electron impinges on matter:




Electron is deflected and decelerated by the atomic nucleus.
(Inelastic scattering)

Deflected electron emits electromagnetic radiation.
Wavelength depends on the loss of energy.


Bremsstrahlung

Continuous spectrum





Bremsstrahlung

Continuous spectrum




Generator Current:
→ Number of Electrons

Characteristic Radiation



Wavelength of $K\alpha_1$, $K\alpha_2$, $K\beta$, $L\alpha$... are characteristic for the atomic species.

X-rays: Spectrum



Old X-ray tubes

Lifetime of a few years:

- Vacuum decreases
→ loss of intensity
- Tungsten from filament deposits on target
→ contaminated spectrum (characteristic W spectrum starts to appear)
- Monitor the intensity
- Replace old tubes


Caution:

Beryllium is toxic & carcinogenic!


- Never touch the windows!
- Use appropriate covers!



X-rays: Summary





- Generated in an X-ray tube
- Spectrum contains Bremsstrahlung (continuous) and characteristic radiation ($K\alpha_1$, $K\alpha_2$, $K\beta$) of target material
- Tube is characterized by:
 - Target material
 - Size and shape of target
 - Acceleration voltage and current




Diffraction Basics

Interaction of X-rays with matter:

- Absorption (photoelectric effect, giving rise to fluorescence)
- Elastic scattering (Thomson scattering)
- ~~Inelastic scattering (Compton scattering)~~



Elastic Scattering




Electron oscillates in the electric field,
emits photons of the same wavelength as
the incoming radiation ($\lambda_s = \lambda_p$).

Secondary wave is in phase
(+ 180°) with primary wave.


Crystal Lattice

Crystal: Periodic arrangement of atoms/ions/molecules in 3 dimensions.




Electrons of each atom become a source of scattered radiation (spherical waves)

Interference pattern




$n=2$

Interference pattern




n=50

Bragg's Law



Lattice Planes and Miller Indices





Definition:

A lattice plane is a plane which intersects atoms of a unit cell across the whole 3-dimensional lattice.

- Each lattice plane generates a diffraction peak.
- The 2θ angle of the peak depends on the plane's d-spacing.
- Diffraction peaks can be labelled with the plane's Miller index.


Bragg's Law

$$\text{CuK}\alpha_1 = 0.154056 \text{ nm}$$
$$a = 0.2 \text{ nm}$$
$$b = 0.5 \text{ nm}$$



Single Crystal


A single crystal must be rotated to bring each lattice plane in diffraction condition.



Polycrystals, Powders

In an ideal powder every possible orientation of crystals occurs.

In a random powder no orientation is preferred.




In an ideal powder all possible diffraction peaks are generated, regardless of sample orientation.



Diffraction Cones


Diffraction at an angle $2\theta^\circ$ from the primary beam



All possible rays form a cone = diffraction cone = Debye cone


Diffraction Cones

Powder sample:




One Debye Cone for each lattice plane spacing (d value)


Debye Ring



Powder Diffractometer




Powder Diffraction Pattern




Monochromatic X-radiation

Diffraction angle θ depends on wavelength λ :


$$n \cdot \lambda = 2 \cdot d \cdot \sin(\theta)$$



We need monochromatic X-radiation!





Monochromatic X-Radiation




Ideally: Isolate K α_1

Reality: Suppress K β and Bremsstrahlung




K β -filtered Diffraction Pattern




LaB₆ pattern, Cu radiation, Ni filter in primary beam (Bruker D8 Advance)

K β -filtered Diffraction Pattern




LaB₆ pattern, Cu radiation, Ni filter in primary beam (Bruker D8 Advance)

Graphite Monochromator




LaB_6 pattern, Cu radiation, Graphite monochromator, secondary beam (PANalytical CubiX³)

Graphite Monochromator




LaB₆ pattern, Cu radiation, Graphite monochromator, secondary beam (PANalytical CubiX³)

Energy-Dispersive Detector




Al₂O₃ pattern, Cu radiation, LynxEyeXE detector (Bruker D8 Advance)

Energy-Dispersive Detector




Al₂O₃ pattern, Cu radiation, LynxEyeXE detector (Bruker D8 Advance)

Energy-Dispersive Detector + K β filter



Al₂O₃ pattern, Cu radiation, LynxEyeXE detector (Bruker D8 Advance)

Energy-Dispersive Detector + K β filter



Al₂O₃ pattern, Cu radiation, LynxEyeXE detector (Bruker D8 Advance)

Monochromators



K β Filter:

Selectively suppresses K β
and parts of Bremsstrahlung


Monochromator crystal and
energy dispersive detector:
Suppress everything BUT K α




Important difference for
fluorescent samples



Ni-Filtered Cu Radiation, Fe Fluorescence



Secondary-monochromated Cu-Radiation



Summary: Monochromators

| Optical Element | Effect on Spectrum | Effect on Intensity |
|----------------------------|--|---|
| K β Filter | Reduces K β peaks | Moderate loss |
| Graphite Monochromator | Eliminates K β peaks Eliminates Fluorescence | Strong loss |
| Multi-bounce Monochromator | Eliminates K β and K α_2 Eliminates Fluorescence | Massive loss (mostly used on Synchrotrons) |
| Energy dispersive Detector | Reduces K β peaks Eliminates Fluorescence | No loss |

Overview of Instruments

| Lab | Instrument | Monochromator |
|----------------|--------------------|-------------------------------|
| RMS Foundation | Bruker D8 | Energy dispersive Detector |
| Uni Bern | Panalytical X'Pert | K β -Filter |
| Uni Bern | Panalytical CubiX | Graphite Monochromator |



Bruker D8



Panalytical X'Pert



Panalytical CubiX